

Application Serial Number 10/748,649  
Reply Dated: 06/01/2007

Regarding Office Action Dated: 03/13/2007

**Amendments to the Claims:**

This listing of claims will replace all prior versions, and listings, of claims in the application:

**Listing of Claims:**

1. (Currently Amended) A product comprising:
  - a single ply web comprising cellulosic fibers having a first and a second opposing sides;
  - ~~a plurality of extruded filaments of a chemical additive having a viscosity between about 1,000 cps to about 50,000 cps~~ topically applied to either the first and/or second opposing side of the web;
  - the single ply web wound into a roll;
  - the roll having a roll bulk about 10 cc/g or greater; and
  - the first and/or second opposing side with the topically applied chemical additive filaments having a Fuzz-On-Edge about 1.8 mm/mm or greater.
2. (Withdrawn/Currently Amended) A product comprising:
  - an uncreped throughdried single ply tissue web comprising cellulosic fibers having a first and a second opposing sides;
  - ~~a plurality of extruded filaments of a chemical additive having a viscosity between about 1,000 cps to about 50,000 cps~~ topically applied to either the first and/or second opposing side of the web;
  - the tissue web wound into a roll;
  - the roll having a roll bulk about 10 cc/g or greater; and
  - the first and/or second opposing side with the topically applied chemical additive filaments having a Fuzz-On-Edge about 2.0 mm/mm or greater.
3. (Original) The product of claim 1 or 2 wherein the roll bulk is about 11 cc/g or greater.

Application Serial Number 10/748,649  
Reply Dated: 06/01/2007

Regarding Office Action Dated: 03/13/2007

4. (Original) The product of claim 1 or 2 wherein the roll bulk is between about 10 cc/g to about 16 cc/g.
5. (Original) The product of claim 1 or 2 wherein the roll bulk is between about 11 cc/g to about 16 cc/g.
6. (Original) The product of claim 1 or 2 wherein the Fuzz-On Edge is about 2.4 mm/mm or greater.
7. (Original) The product of claim 1 or 2 wherein the Fuzz-On Edge is about 2.8 mm/mm or greater.
8. (Original) The product of claim 1 or 2 wherein the Fuzz-On Edge is between about 2.0 mm/mm to about 3.0 mm/mm.
9. (Original) The product of claim 1 or 2 wherein the web comprises a bath tissue web.
10. (Currently Amended) The product of claim 1 or 2 wherein the extruded filaments of the chemical additive is are topically applied to both the first and the second opposing sides.
11. (Original) The product of claim 5 wherein the Fuzz-On Edge is between about 2.0 mm/mm to about 3.0 mm/mm.
12. (Original) The product of claim 5 wherein the Fuzz-On Edge is between about 2.2 mm/mm to about 2.9 mm/mm.
13. (Original) The product of claim 1 or 2 wherein the chemical additive comprises polysiloxane.
14. (Original) The product of claim 1 or 2 wherein the Kershaw firmness is between about 12 mm to about 0 mm.
15. (Original) The product of claim 1 or 2 wherein the CD Kawabata Bending Stiffness is about 0.06 or less.
16. (Original) The product of claim 11 wherein the CD Kawabata Bending Stiffness is about 0.04 or less.

Application Serial Number 10/748,649  
Reply Dated: 06/01/2007

Regarding Office Action Dated: 03/13/2007

17. (Currently Amended) The product of claim 1, 2, 5, 10, 11, 13, 14, 15, or 16 wherein the first or second opposing side with the applied chemical contains a plurality of fuzzy fibers generated by a shear calendering device ~~and the chemical additive is applied as a plurality of chemical filaments.~~
18. - 21. (Canceled)
22. (Previously presented) The product of claim 1 or 2 wherein the chemical additive has a viscosity of between about 1,500 cps to about 10,000 cps.
23. (Currently Amended) The product of claim 1 or 2 wherein the ~~chemical additive on the first or second opposing side comprises a plurality of filaments forming~~ extruded filaments form a network.
24. (New) The product of claim 1 or 2 wherein the chemical additive has a viscosity of between about 1,000 cps to about 50,000 cps.
25. (New) The product of claim 1 or 2 wherein the extruded filaments of the chemical additive are topically applied to only one opposing side of the web.
26. (New) The product of claim 1 or 2 wherein extruded filaments are continuous.
27. (New) The product of claim 1 or 2 wherein the extruded filaments are discontinuous.
28. (New) The product of claim 1 or 2 wherein the extruded filaments are melt blown.